

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>H01M 8/02</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 97/50139</b> <b>(43) International Publication Date:</b> 31 December 1997 (31.12.97)
<b>(21) International Application Number:</b> PCT/US97/11073 <b>(22) International Filing Date:</b> 25 June 1997 (25.06.97) <b>(30) Priority Data:</b> 8/182700 25 June 1996 (25.06.96) JP <b>(71) Applicant:</b> E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). <b>(72) Inventors:</b> MUKOHYAMA, Atsushi; 4199-1-509, Nagatsuda-cho, Midori-ku, Yokohama-shi, Kanagawa (JP). TAKEDA, Toshihiko; Purimale Azamino 106, 1-23-17, Shin-Ishikawa, Aoba-ku, Yokohama-shi, Kanagawa 225 (JP). UCHIDA, Makoto; 2-16-2, Koganeno Hirakata-shi, Osaka 573 (JP). FUKUOKA, Yuko; 65-1-308, Nishidera-cho, Ohkamedani, Fukakusa, Fushimi-ku, Kyoto 612 (JP). <b>(74) Agent:</b> HENDRICKSON, John, S.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		<b>(81) Designated States:</b> CA, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> POLYMER ELECTROLYTE MEMBRANE FUEL CELL WITH BIPOLAR PLATE HAVING INTEGRALLY MOLDED CONDUCTIVE INSERT  <b>(57) Abstract</b>  A polymer electrolyte membrane fuel cell comprised of polymer electrolyte membranes, gas diffusion electrodes that sandwich the membranes, and bipolar plates operating as gas separation plates and current collectors with fuel/oxidizing agent supply and discharge passages. A bipolar plate is employed comprising a frame of melt-processible polymer of good fluidity and with superior acid and hydrolytic resistance and a carbon plate or corrosion-resistant conductive plate integrally molded into the frame. The carbon or corrosion-resistant metal plate has concave and convex parts on both surfaces which provide the fuel/oxidizing agent supply and discharge passages when the bipolar plate is in contact with the gas diffusion electrodes.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## **TITLE**

Polymer Electrolyte Membrane Fuel Cell with Bipolar Plate Having Integrally Molded Conductive Insert

## **FIELD OF THE INVENTION**

This invention relates a polymer electrolyte membrane fuel cell for direct generation of electrical energy from fuel and an oxidizing agent and, especially, it relates to a bipolar plate structure for a fuel cell that has a high degree of resistance to corrosive electrolytes and is easily manufactured.

## **BACKGROUND OF THE INVENTION**


In recent years, polymer electrolyte membrane fuel cells have been developed for their advantages over conventional electrical power sources in high power generation, high efficiency, etc. Polymer electrolyte membrane fuel cells typically have a multiplicity of unit cells in an stacked arrangement, each comprised of a cathode and an anode which are opposingly positioned gas diffusion electrodes. A polymer electrolyte membrane is located between and is maintained in contact with the electrodes. Bipolar plates are provided between cells and contact the gas diffusion electrodes of adjacent cells and each side of the bipolar plate provides gas passages to the electrode. A fuel cell generates power through electrochemical reaction between the anode and cathode when supplying fuel and oxidizing agent to the fuel passages on the anode side and the oxidizing agent chamber on the cathode side, respectively.

In a fuel cell, when fuel and oxidizing agent are independently and simultaneously supplied to the different electrodes, an electrochemical potential is generated across these electrodes. When an electrical load is placed across these electrodes, a current flows between them and, as a result, chemical energy is directly converted to electrical energy at high efficiency as mentioned above, by having the fuel oxidized at one electrode and the oxidizing agent reduced at the other electrode, both in an electrocatalytic manner.

The polymer electrolyte membrane in such fuel cells is advantageously provided by a high molecular weight ion-exchange fluorine-containing polymer having one or more functional groups which can be sulfonic acid groups, carboxylic acid groups, phosphoric acid groups or phosphonic acid groups. The polymer of the ion-exchange membrane of the electrolyte is preferably a copolymer of tetrafluoroethylene and fluorovinyl compound which is expressed by  $\text{CF}_2=\text{CF}-(\text{OCF}_2\text{CFX})_m-\text{O}_q-(\text{CF}_2)_n\text{A}$  (where  $m=0-3$ ,  $n=0-12$ ,  $q=0$  or  $1$ ,

X=F or CF<sub>3</sub>, A=a sulfonic acid functional group, a carboxylic-acid functional group, a phosphoric acid functional group).

Preferable examples of such fluorovinyl compounds can be:



Alternatively, perfluoroolefins, such as hexafluoropropylene, chlorotrifluoroethylene, perfluoroalkoxyvinyl ether can be used instead of the tetrafluoroethylene, as the monomer that comprises the fluorocarbon polymer with functional groups.

If necessary after copolymerization, the polymer is converted to a proton-exchanging functional group, for example, by post-treatment such as hydrolysis, etc. The conversion capacity of a component with functional group is defined by the number of moles of the functional group per 1 g and normally it is measured by the titration method. In general, a conversion capacity of the component with functional group of 0.8-2 meq/g and 0.9-2 meq/g is preferred. When it is less than 0.8 meq/g, the resistance becomes high and performance suffers. Also, when it is above 2 meq/g, the standard strength of the membrane is decreased.

Sulfonated perfluorocarbon membrane such as that commercially available from E.I. du Pont de Nemours and Company, Wilmington, Delaware, USA, under the trademark NAFION® is advantageously used as the polymer electrolyte membrane because of its strength, dimensional stability and electrical properties.

Bipolar plates in polymer electrolyte fuel cells are typically machined from a carbon block with strong corrosion resistance, no gas permeability and with good electrical conductivity. The fuel/oxidizing agent supply and discharge passages are machined on both sides of the bipolar plate and, since the concave/convex shape and layout of the concave/convex parts of the bipolar plate of these passages determine the uniform distribution of the gas flow at a uniform density onto the electrode surface, the structures are extremely complex. Therefore, manufacture of bipolar plates is very difficult. In addition, when a bipolar plate is made of standard grade carbon, a leak current sometimes runs in the bipolar plate across the electrolyte and electrodes and corrosion can occur in the bipolar plate. It has been difficult to manufacture from a single material of a bipolar plate for polymer electrolyte fuel cells which exhibits a high degree of

resistance to the corrosive electrolyte, has good current collection function and a high degree of structural integrity.

### **SUMMARY OF THE INVENTION**

5           The invention is an improvement in a polymer electrolyte membrane fuel cell comprised of polymer electrolyte membranes, gas diffusion electrodes that sandwich the membranes, and bipolar plates operating as gas separation plates and current collectors with fuel/oxidizing agent supply and discharge passages. An improved bipolar plate is employed comprising a frame of melt-processible  
10   polymer of good fluidity and with superior acid and hydrolytic resistance and a carbon plate or corrosion-resistant conductive plate integrally molded into the frame. The carbon or corrosion-resistant metal plate has concave and convex parts on both surfaces which provide the fuel/oxidizing agent supply and discharge passages when the bipolar plate is in contact with the gas diffusion  
15   electrodes.

          In a preferred form of the present invention, the frame comprises a polymer selected from liquid crystal polymers, a modified polyphenylene oxide, a polyphenylene sulfide, thermoplastic fluorine resins and polyolefins. More preferably, the polymer of the frame is selected from liquid crystal polymers and  
20   polyolefins.

          In another preferred form of the present invention, the bipolar plate comprises a corrosion-resistant conductive plate which is a corrosion resistant metal plate or a metal plate surface treated with metal carbide or metal nitride.

          In another preferred form of the present invention, the frame is formed  
25   using insert molding.

          This invention provides a polymer electrolyte membrane fuel cell in which a bipolar plate is formed by a melt-processible polymer of good fluidity, good acid and hydrolytic resistance, and current collection function, and with improvement of the gas-passages. This is accomplished while providing  
30   resistance to corrosive electrolytes, simple construction, easy manufacturing, reduced weight, and low manufacturing cost. The bipolar plates used in a preferred fuel cell in accordance with the invention provide high strength, high elasticity, good dimensional stability, good corrosion resistance, a high degree of structural integrity and good core properties.

35

### **BRIEF DESCRIPTION OF THE FIGURES**

Figure 1 is perspective view which illustrates a preferred polymer electrolyte membrane fuel cell in accordance with this invention as described in more detail in the Example.

5

Explanation of the codes:

- 1 - bipolar plate
- 2 - carbon plate or metal plate surface treated with metal carbide or metal nitride
- 3 - polymer frame
- 10 4 - high molecular electrolyte membrane
- 5 - cathode
- 6 - anode.

Figure 2 is a log/log plot of melt viscosity against shear rate for a preferred liquid crystal polymer useful in the manufacture of the polymer frame for the bipolar plate in a fuel cell in accordance with the present invention.

15

### **DETAILED DESCRIPTION**

In the polymer electrolyte membrane fuel cell of this invention, the frame of the bipolar plate that surrounds the carbon plate or corrosion-resistant conductive plate with concave and convex parts, is injection-molded with a melt-processible polymer of good fluidity and having good acid resistance and hydrolysis resistance. Preferred molding methods include insert molding, press fitting, and caulking. Among above molding methods, the insert molding method is most preferable for this invention. The carbon plate or corrosion-resistant conductive plate, preferably, metal plate or metal plate treated with metal carbide or metal nitride, is set and closed in an injection molding cavity-die having core and cavity dies. Such integrally molded bipolar plate has good strength, high elasticity, good dimensional stability, high heat resistance, corrosion resistance, a high degree of structural integrity and core properties. In addition, size/weight reduction and reduction of manufacturing costs is provided for fuel cells of laminated unit cells comprised of such bipolar plate and membrane electrode composites consisting of a cathode, anode, and electrolyte.

20

25

30

35

Examples of melt-processible polymers with good fluidity and with good acid resistance, hydrolytic resistance and fluidity for molding of the frame can be a liquid crystal polymer, a modified polyphenylene oxide, a polyphenylene sulfide, thermoplastic fluorinated resins and polyolefins. However, the polymer is not limited to the polymers listed above as long as properties are maintained for a long period at 50-80°C and in saturated water vapor, which are the normal

operating conditions of this fuel cell. A polymer with good fluidity has a sufficiently high flow at its normal processing temperature to form the polymer frame. Liquid crystal polymers are especially preferred since they are highly resistant to hydrolysis, have excellent fluidity needed for molding and are optimal for the production of fine structures as those of this invention. Also, liquid crystal polymers have an extremely low metal ion content as compared to other polymers; therefore, they do not inhibit ion conduction of the polymer electrolyte membrane. Preferable components of a suitable liquid crystal polymer are selected from the compounds: i) comprised of 1 or more aromatic dicarboxylic acid and alicyclic dicarboxylic acid; ii) comprised of 1 or more aromatic diol, alicyclic diol and aliphatic diol; iii) comprised of 1 or more aromatic hydroxycarboxylic acid; iv) comprised of 1 or more aromatic thiol carboxylic acid; v) comprised of 1 or more aromatic dithiol and aromatic thiolphenol, and; vi) comprised of 1 or more aromatic hydroxylamine and aromatic diamine, etc., and polymers that form anisotropic molten phases are polyesters that form anisotropic molten phase, comprised of a combination of a) polyester of (i) and (ii); b) polyester of only (iii); c) polyester of (i), (ii), and (iii); d) polydiol ester of only (iv); e) polythiol ester of (i) and (v); f) polythiol ester of (i), (iv), and (v); g) polyester amide of (i), (iii) and (vi); h) polyester amide of (i), (ii), (iii), and (vi), etc.

For a liquid crystal polymer such as the polyester-type polymer sold by E.I. du Pont de Nemours and Company under the trademark ZENITE® HX 6130, typical molding conditions for the formation of the frame are, for example, 60°C die temperature, 350-360°C resin temperature, 0.5-1 sec pressure retention time and approximately 10 sec molding cycle. Figure 2 is a log/log plot of melt viscosity against shear rate for ZENITE® HX 6130 liquid crystal polymer which demonstrates the good fluidity possessed by this polymer. The good fluidity of ZENITE® HX 6130 (30% glass reinforced LCP) is also illustrated by its spiral flow of 24 cm flow for 0.5 mm thickness under 800 kg/cm<sup>2</sup> at 355°C. Spiral flow is determined by measuring the distance that the molten polymer flows into a specific thickness mold with a spiral shape at 60°C.

CRASTIN® SK645FR 30% glass reinforced polybutylene terephthalate polymer sold by E.I. du Pont de Nemours and Company also has good fluidity for use in the present invention with a spiral flow of 7.0 cm flow for 0.8 mm thickness under 800 kg/cm<sup>2</sup> at 255°C.

Polyethylene is produced by polymerization of ethylene and is a mixture with a few to a few hundred thousand basic molecular unit -(CH<sub>2</sub>)- connected in a chain form, and it is considered to be a long chain hydrocarbon with a molecular weight distribution. When the average molecular weight


increases, the softening point increases a little. There are the following types of polyethylene, depending on the manufacturing method. Polyethylene is manufactured by direct polymerization of ethylene gas, but it can be produced under high pressure, medium pressure, or low pressure, each method produces polyethylene with slightly different properties.

Polyethylene obtained by the high-pressure method has a density of 0.91-0.94, that obtained by the medium/low pressure method has a density of 0.91-0.97 in a wider range, and, in this wider range, that having  $\geq 0.94$  density and that having  $< 0.94$  density re classified as high-density polyethylene and linear low-density polyethylene, respectively. The molding conditions of polyethylene are, in general, 150-210°C resin temperature, 40-50°C mold temperature and 20-40 seconds molding cycle.

Polypropylene is a crystalline polymer material in which the polypropylene units  $-(CH_2CH(CH_3))-$  are regularly and spatially arranged and its specific gravity is next lightest to that of polymethylpentene. Its melting point is 165°C and it has good compressive strength, impact strength and high surface hardness. It is fluid and it can be molded into a thin or complex shape. Its shrinkage in molding is less than that of polyethylene and its bi-directional shrinkage difference is small. General molding conditions of polypropylene are 190-230°C resin temperature, 40-80°C mold temperature, and 20-40 second molding cycle.

Polystyrene is a polymer produced by polymerization of a styrene monomer  $-(CH_2-CH(C_6H_5))-$  and has good moldability, transparency, dimensional stability, and water resistance. Also, it is highly resistant to chemicals such as those of acid and alkali groups. The molding conditions of polystyrene are 200-230°C resin temperature, 30-50°C mold temperature, and 30-60 second molding cycle.

Polymethylpentene is 4-methylpentene-1, polymerized with a Ziegler-Natta catalyst, and has the following structure:



Its melting point is 230-240°C, and its specific gravity is 0.83 which is the lightest among the thermoplastic resins. Its chemical resistance is also good.

When the insert plate is a carbon material, carbon, graphite, glassy carbon, high density isotropic carbon, carbon fiber, or graphite foil can be used.



As a corrosion resistant conductive plate, a corrosion resistant metal, a metal plate surface treated with metal carbide or metal nitride, a metal or a carbon with its corrosion resistance or conductance being improved by using a surface treatment such as plating, chemical vapor deposition (CVD) or sputtering or plating with platinum or gold or other corrosion resistant metal can be used for this invention. From the viewpoint of production cost and ease of manufacture, a corrosion resistant metal plate with its surface treated with metal carbide or metal nitride are preferable.

10

### **EXAMPLE**

An embodiment of a polymer electrolyte membrane fuel cell of this invention is described below with the aid of Figure 1.

The bipolar plate 1 in Figure 1 is comprised of a carbon plate, metal plate or metal plate 2, surface treated with metal carbide or metal nitride, in each case having concave parts and convex parts on both sides and polymer frame 3 that surrounds the above plate. This carbon plate, or metal plate, or metal plate 2 surface treated with metal carbide or metal nitride is inserted into the laminated cell unit so that the tips of the protruding parts make contact with the outside electrode of the membrane electrode component 7. For example, anode 6 and cathode 5, which are integrally formed with the high molecular weight electrolyte membrane, sandwich the membrane 4 for collection of electricity. The fuel chambers are formed between the concave part of the carbon plate or metal plate 2 and the anode 6. An oxidizing agent chamber will be similarly formed by the concave parts on the other side of the plate 2 in contact with cathode 5. The bipolar plate 1 can be used as the end plate of the stack and, when membrane electrode composites 7 are laminated between bipolar plates 1, the concave parts of carbon plate or metal plate 2, assures the gas supply passage to the surfaces of cathode 5 and anode 6. In addition, as shown in Figure 1, the polymer frame 3 has through-holes 8 that connect through the frame to each gas passage means to supply fuel to the fuel chamber. Similar through-holes 9 are located at corresponding positions in opposing end faces of polymer frame 3 and supply an oxidizing agent to the oxidizing agent chamber.

35

### **MANUFACTURING METHOD**

The carbon plate or metal plate or metal plate 2 surface treated with metal carbide or metal nitride having concave parts and convex parts on both sides is set in the injection molding cavity die. The die is closed and the melt-processible polymer of good fluidity and good hydrolysis resistance, e.g. liquid

crystal polymer, is injected into the cavity for molding of frame 3 that surrounds carbon plate or metal plate or metal plate 2 surface treated with metal carbide or metal nitride. A bipolar plate 1 with an integral insert molding is formed with carbon plate or metal plate 2 positioned in its center.

5

**WHAT IS CLAIMED IS:**

1. In a polymer electrolyte membrane fuel cell comprised of polymer electrolyte membranes, gas diffusion electrodes that sandwich the membranes, and bipolar plates operating as gas separation plates and current collectors with  
5 fuel/oxidizing agent supply and discharge passages, the improvement comprising a bipolar plate having a frame of melt-processible polymer of good fluidity and with superior acid and hydrolytic resistance and a carbon plate or corrosion-resistant conductive plate integrally molded into said frame, said carbon or corrosion-resistant metal plate having concave and convex parts on both surfaces  
10 which provide said fuel/oxidizing agent supply and discharge passages when said bipolar plate is in contact with said gas diffusion electrodes.
2. The polymer electrolyte membrane fuel cell of Claim 1 wherein said frame comprises a polymer selected from the group consisting of liquid crystal polymers, a modified polyphenylene oxide, a polyphenylene sulfide,  
15 thermoplastic fluorinated resins and polyolefins.
3. The polymer electrolyte membrane fuel cell of Claim 1 wherein said frame comprises a polymer selected from the group consisting of liquid crystal polymers and polyolefins.
4. The polymer electrolyte membrane fuel cell of Claim 1 wherein  
20 said bipolar plate comprises a corrosion-resistant conductive plate, said corrosion-resistant conductive plate comprising a corrosion resistant metal plate or a metal plate surface treated with metal carbide or metal nitride.
5. Polymer electrolyte membrane fuel cell of Claim 1 wherein said frame is formed using insert molding.

# INTERNATIONAL SEARCH REPORT

Interr. Application No  
PCT/US 97/11073

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 H01M8/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 014, no. 085 (E-0890), 16 February 1990 & JP 01 296569 A (HITACHI LTD), 29 November 1989, see abstract & CHEMICAL ABSTRACTS, vol. 113, no. 12, 17 September 1990 Columbus, Ohio, US; abstract no. 100895, see abstract	1-3
Y	---	4,5
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

29 October 1997

Date of mailing of the international search report

14. 11 97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

D'hondt, J

# INTERNATIONAL SEARCH REPORT

Intern: al Application No

PCT/US 97/11073

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 012, no. 099 (E-594), 31 March 1988 & JP 62 229765 A (SHIN KOBE ELECTRIC MACH CO LTD), 8 October 1987, see abstract & CHEMICAL ABSTRACTS, vol. 108, no. 4, 25 January 1988 Columbus, Ohio, US; abstract no. 24609, see abstract	1-5
Y	---	1,4,5
Y	US 3 589 942 A (LEITZ FRANK B JR ET AL) 29 June 1971 see column 3, line 12 - line 16; claims 1,10 see column 3, line 56 - line 61	1,4
X	---	1
X	PATENT ABSTRACTS OF JAPAN vol. 015, no. 050 (E-1030), 6 February 1991 & JP 02 281567 A (HITACHI LTD), 19 November 1990, see abstract & CHEMICAL ABSTRACTS, vol. 114, no. 26, 1 July 1991 Columbus, Ohio, US; abstract no. 250724, see abstract	1
X	---	1
X	PATENT ABSTRACTS OF JAPAN vol. 011, no. 138 (E-503), 2 May 1987 & JP 61 279069 A (HITACHI LTD), 9 December 1986, see abstract & CHEMICAL ABSTRACTS, vol. 106, no. 16, 20 April 1987 Columbus, Ohio, US; abstract no. 123151, see abstract	1
A	---	1-3,5
A	US 4 124 478 A (TSIEN HSUE C ET AL) 7 November 1978 see column 2, line 59 - column 3, line 48; figures 1-4 see column 2, line 1 - line 13 see column 7, line 45 - line 50	1-3,5
A	---	1
2	DE 43 09 976 A (DAIMLER BENZ AG) 29 September 1994 see column 2, line 22 - line 26; claims 1-3; figure 1	1
	---	-/--

# INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/US 97/11073

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	R.H.BLACKMER ET AL: "Ion-exchange membrane" ASE JOURNAL, vol. 70, no. 1, January 1962, pages 82-86, XP002044995 see page 82, left-hand column, paragraph 2 see page 83, left-hand column, paragraph 1 - paragraph 2; figures 4,5 ---	6
A	PATENT ABSTRACTS OF JAPAN vol. 096, no. 010, 31 October 1996 & JP 08 162131 A (AISIN AW CO LTD;AQUEOUS RES:KK), 21 June 1996, see abstract ---	1
A	US 5 187 025 A (KELLAND JAMES W ET AL) 16 February 1993 see column 4, line 6 - line 16 see column 1, line 7 - line 10 ---	2
A	WO 93 13566 A (INT FUEL CELLS INC) 8 July 1993 see claims 1,3,4; figures 1,2 ---	2
A	WO 96 18217 A (FRAUNHOFER GES FORSCHUNG ;LEDJEFF KONSTANTIN (DE); NOLTE ROLAND (D) 13 June 1996 see page 13, line 34 - page 14, line 30; figure 7 ---	2
A	CHEMICAL ABSTRACTS, vol. 101, no. 16, 15 October 1984 Columbus, Ohio, US; abstract no. 134012, XP002044996 see abstract & PROC.-ELECTROCHEM. SOC., vol. 84, no. 5, 1984, pages 554-573, -----	4

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/11073

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3589942 A	29-06-71	NONE	
US 4124478 A	07-11-78	NONE	
DE 4309976 A	29-09-94	DE 59403595 D EP 0620609 A	11-09-97 19-10-94
US 5187025 A	16-02-93	NONE	
WO 9313566 A	08-07-93	US 5523175 A	04-06-96
WO 9618217 A	13-06-96	DE 4443939 C EP 0797848 A	29-08-96 01-10-97